

Claims

- 000221" 24965250
1. A thermoforming mold having a surface roughness (Ra) of not more than $0.1\mu\text{m}$.
2. A thermoformed article comprising a crystalline olefin resin, which article has a surface roughness (Ra) of not more than $3\mu\text{m}$.
3. The thermoformed article according to Claim 2, wherein the olefin resin contains a propylene homopolymer.
4. The thermoformed article according to Claim 2, wherein the olefin resin contains a propylene homopolymer having an mmmm pentad % of not less than 0.95.
5. The thermoformed article according to Claim 2, wherein the thermoformed article is a sheet having a thickness of from 50 to $700\mu\text{m}$.
6. The thermoformed article according to Claim 2, wherein the thermoformed article has a total haze of not more than 5% and an inner haze of not more than 3%.
7. A process for producing a thermoformed article, which comprises the steps of:
- (i) heating and softening a crystalline olefin resin to obtain a sheet thereof; and

(ii) thermoforming the sheet with a thermoforming mold having a surface roughness (Ra) of not more than $0.1\mu\text{m}$ to obtain a thermoformed article having a surface roughness (Ra) of not more than $3\mu\text{m}$.

5

8. The process for producing a thermoformed article according to Claim 7, wherein the olefin resin contains a propylene homopolymer.

10

9. The process for producing a thermoformed article according to Claim 7, wherein the olefin resin contains a propylene homopolymer having an mmmmm pentad % of not less than 0.95.

15

10. The process for producing a thermoformed article according to Claim 7, wherein the thermoformed article is a sheet having a thickness of from 50 to $700\mu\text{m}$.

20

11. The process for producing a thermoformed article according to Claim 7, wherein the thermoformed article has a total haze of not more than 5% and an inner haze of not more than 3%.

25

12. A laminated molding article, which comprises:

(i) a thermoformed article containing a crystalline olefin resin, and having a surface roughness (Ra) of not more than $3\mu\text{m}$; and

(ii) a substrate containing a crystalline olefin resin.

00022T 24966600

Handwritten: 428
336

13. The laminated molding article according to Claim 12, wherein the olefin resin contains a propylene homopolymer.

5 14. The laminated molding article according to Claim 12, wherein the olefin resin contains a propylene homopolymer having an ~~mmmm~~ pentad % of not less than 0.95.

10 15. The laminated molding article according to Claim 12, wherein the thermoformed article is a sheet having a thickness of from 50 to 700 μ m.

15 16. The laminated molding article according to Claim 12, wherein the thermoformed article has a total haze of not more than 5% and an inner haze of not more than 3%.

17. The laminated molding article according to Claim 12, wherein the laminated molding article is a car part.

20 18. The laminated molding article according to Claim 12, wherein the laminated molding article is a center cluster.

19. A process for producing a laminated molding article, which comprises the steps of:

25 (i) heating and softening a crystalline olefin resin to obtain a sheet thereof;

(ii) thermoforming the sheet with a thermoforming mold having a surface roughness (Ra) of not more than 0.1 μ m to

000221 24962650

according to Claim 19, wherein the laminated molding article
is a car part.

25. The process for producing a laminated molding article
5 according to Claim 19, wherein the laminated molding article
is a center cluster.

Adg
3